

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : B32B 27/32		A1	(11) International Publication Number: WO 00/54968
			(43) International Publication Date: 21 September 2000 (21.09.00)
(21) International Application Number: PCT/US00/07116		(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).	
(22) International Filing Date: 16 March 2000 (16.03.00)			
(30) Priority Data: 09/271,226 17 March 1999 (17.03.99) US			
(71) Applicant: MOBIL OIL CORPORATION [US/US]; P.O. Box 2149, Baytown, TX 77522-2149 (US).			
(72) Inventors: HEFFELFINGER, Michael, T.; 340 Double Springs Way, Alpharetta, GA 30004 (US). KEUNG, Jay, K.; 503 East St. Ext., Victor, NY 14564 (US). PEET, Robert, G.; 44 Sunset Boulevard, Pittsford, NY 14534-2143 (US).			
(74) Agents: SIMMONS, T., Dean et al.; ExxonMobil Chemical Company, P.O. Box 2149, Baytown, TX 77522-2149 (US).		<p>Published</p> <p><i>With international search report.</i></p> <p><i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i></p>	
(54) Title: MULTI-LAYER FILM WITH CORE LAYER OF SYNDIOTACTIC POLYPROPYLENE			
(57) Abstract			
<p>The present invention is directed to a biaxially oriented multi-layer film which comprises: (a) a core layer comprising a syndiotactic propylene polymer homopolymer; and (b) at least one additional layer adjacent to the core layer comprising a polymer which is an ethylene or a propylene homopolymer, ethylene copolymer or terpolymer containing comonomers of propylene and/or butene-1. Optionally, there can be a skin layer applied to the exposed surface of the outer layer. The skin layer and/or the at least one additional layer is a polyolefin selected from the group consisting of isotactic polypropylene, polyethylene, ethylene-propylene random copolymer, ethylene-propylene block copolymer or ethylene-propylene-butene-1 terpolymer.</p>			

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

**MULTI-LAYER FILM WITH CORE LAYER OF
SYNDIOTACTIC POLYPROPYLENE**

FIELD OF THE INVENTION

5 The present invention relates to a multi-layer thermoplastic film having a core layer of syndiotactic polypropylene.

BACKGROUND OF THE INVENTION

 Oriented polypropylene films are known for use in packaging operations.

10 U.S. Patent No. 4,604,324 to Nahmias, et al. discloses a multi-layer polypropylene film structure comprising coextruded layers of a base layer of high stereoregularity polypropylene and a skin layer of comparatively low stereoregularity which contains anti-stick additives. In addition, the skin layer can contain up to 10 wt.% of a wax to improve heat seal characteristics or optical properties of the film. U.S. Patent No.

15 5,254,394 to Bothe, et al., discloses a polyolefin film for packaging comprising isotactic polypropylene base layer and a top layer of syndiotactic polypropylene which has high sealed-seam strength and excellent optical properties. The layers may contain lubricant additives such as waxes at levels of up to 2 wt%, relative to each layer.

20

SUMMARY OF THE INVENTION

 The present invention relates to an oriented multi-layer film which comprises:

- (a) a core layer comprising syndiotactic propylene polymer; and
 - (b) at least one additional layer adjacent to the core layer comprising
- 25 an ethylene or propylene homopolymer, an ethylene copolymer, a terpolymer containing propylene, ethylene, and butene-1 as comonomers, or a blend thereof.

 The polymer of the at least one additional layer can be made by any conventional method such as Ziegler-Natta catalysis or metallocene catalysis.

When the at least one additional layer comprises a blend of polymers, such blend can comprise, e.g., ethylene and/or propylene homopolymers and/or one or more copolymers or terpolymers of propylene with ethylene and/or butene-1.

The present invention is further directed to a process for preparing an oriented multi-layer film which comprises the steps of

(a) melt coextruding a film comprising: (i) a core layer comprising syndiotactic polypropylene, and (ii) at least one additional layer adjacent the core layer comprising an ethylene or propylene homopolymer, an ethylene copolymer, a terpolymer containing propylene, ethylene and butene-1 as comonomers, or a blend thereof; and

(c) orienting the coextruded combination.

In several possible applications, it would be desirable to create films that have properties of the type that would be achieved by making those films from syndiotactic polypropylene. Some of these characteristics, such as the very slow development of its crystalline structure, make it impossible to make a monolayer film of syndiotactic polypropylene, however. What we have found is that the syndiotactic monolayer web extruded from a die onto a casting drum sticks very tightly to the casting drum. Because the crystalline development is very slow, the web distorts unacceptably under the low forces that are used in the accepted methods for pulling the web free from the drum.

We have determined that we can solve this problem and produce a film that can have about as much of the desired properties of a syndiotactic polypropylene film as we choose. This is accomplished by coextruding a layer of isotactic polypropylene, made either by the standard Ziegler-Natta catalyst system or by metallocene catalysts, on at least the side of the cast web that would otherwise contact the casting drum. The degree that the resulting film approximates a monolayer syndiotactic polypropylene film depends, to a large extent, on what fraction of the total structure is made up of syndiotactic polypropylene and what

fraction is isotactic polypropylene, i.e., how thin or how thick a skin layer of isotactic polypropylene one chooses to use.

We have also determined that we can extend this concept so that a film with a core layer of syndiotactic polypropylene can be produced along with intermediate layers of isotactic polypropylene and outer layers of other polymeric materials providing additional characteristics, such as sealability.

DETAILED DESCRIPTION OF THE INVENTION

The core layer is made from syndiotactic polypropylene. The syndiotactic polypropylene generally possesses a syndiotacticity of at least 70% based on racemic pentads, typically greater than 75%, as measured by C^{13} NMR spectroscopy. The mean length of sequence n_r of the syndiotactic sequences is preferably greater than about 20, more preferably greater than about 25.

Commercially available syndiotactic propylene polymers suitable for use in the present invention include EOD 95-01 and 95-02, available from Fina Oil and Chemical Company. These materials have melt flows of about 4 and 7 g/10 min, respectively, as measured in accordance with the standard ASTM D1238 method.

The syndiotactic propylene polymer can, optionally, contain other monomeric units as in the case of a copolymer of propylene with ethylene or α -olefin having from 4 to 20 carbon atoms such as butene-1, pentene-1, hexene-1, heptene-1 or 4-methylpentene-1. Typically, the amount of monomer other than propylene is no more than 10% by weight of the entire polymer.

Propylene polymers having a syndiotactic structure are described in U.S. Patent Nos. 5,254,394; 5,254,384; 5,162,278; 5,155,080; 4,892,851 and European Patent No. 0499216, all of which are incorporated herein by reference.

The propylene polymer is usually predominantly comprised of propylene (at least 90% by weight) and has a melting point of about 140°C or higher, more typically a melting point of 150°C or higher. The melt flow rate usually ranges from

about 0.5 g/10 min to about 15 g/10 min at 230°C, more typically about 1.5 g/10 min to about 4 g/10 min at 230°C. The melt flow rate is measured according to the standard procedure set forth in ASTM D1238.

5 The at least one additional layer of the present invention may be any one of the coextrudable, biaxially orientable film-forming resins known in the art. Such materials include, but are not limited to, isotactic polypropylene, other syndiotactic polypropylenes, ethylene copolymers and terpolymers which include other monomers such as propylene and/or butene-1. Typical copolymers are ethylene-propylene copolymers, ethylene-butene-1 copolymers, butene-1-propylene random
10 copolymers, and ethylene-propylene block copolymers. Typical terpolymers are ethylene-propylene-butene-1 terpolymers. Alternative and useful thermoplastic materials for the at least one additional layer include, but are not limited to nylon, polyester, ethylene-vinyl acetate copolymer, and ethylene-vinyl alcohol copolymer. Blends of any of the foregoing homopolymers, copolymers and terpolymers are
15 contemplated.

Ethylene-propylene-butene-1 random terpolymers appropriate for use in the at least one additional layer of the present invention include those containing 1-5 weight percent random ethylene and 10-25 weight percent random butene-1, with the balance being made up of propylene. The amounts of the random ethylene and
20 butene-1 components in these terpolymers are typically in the range of 10 to 25 weight percent (ethylene plus butene-1) based on the total amount of the copolymer.

The copolymers and terpolymers typically have a melt flow rate in the range of about 5 to 10 g/10 min, with a density of about 0.9 and a melting point in the range of about 115 to about 130°C.

25 The polymers of the outermost layers of the film can also be fabricated from any polymers, copolymers or terpolymers or blends of homopolymers and blends of copolymer(s) and homopolymer(s) which have heat seal properties. Several of the

materials identified above are illustrative of heat sealable copolymers which can be used in the present invention.

In one aspect of the invention there is at least one additional layer is derived from polyethylene. The polyethylene can be low density polyethylene (LDPE), linear low density polyethylene (LLDPE), medium density polyethylene (MDPE) or high density polyethylene (HDPE). These ethylene polymers typically have a melt index ranging from about 0.3 to about 15 g/10 min, as measured in accordance with the standards of ASTM D1238. The low density polyethylenes should have a density of about 0.88 to about 0.93 g/cm³. Linear materials may have a density as high as 0.94 g/cm³, often ranging from 0.90 to 0.94 g/cm³, with a melt index of about 1 to about 10. The linear low density polyethylenes may be derived from ethylene together with other higher comonomers such as butene-1, hexene-1, or octene-1. Typically it is useful to use HDPE as the at least one additional layer as it enhances film toughness. HDPE has a density of greater than about 0.941 g/cm³, typically from about 0.941 to about 0.965 g/cm³. High density polyethylene suitable for use as the at least one additional layer is described in Bakker, Ed. "The Wiley Encyclopedia of Packaging Technology, pp. 514 to 523 (1986).

Each of the at least one additional layer can range in thickness from about 0.01 mil to about 0.20 mil, specifically from about 0.02 mil to about 0.06 mil.

There can be more than one layer coextruded on each side of the core. That is, one or more layers, selected from the materials defined for the at least one additional layer, can be added to one or both surfaces of the core layer. Films having such a multi-layer structure are represented, in simplified form, as having a structure "ABCDE" where "C" represents a core layer, "B" represents an outer layer adjacent to the core layer and "A" represents a further outer layer or skin layer applied to the outer surface of outer layer "B." In such a film structure, the outer layer "B" can be referred to as a "tie-layer" or an "intermediate layer." Layers "A" and "B" may be the same or different. Similarly, "D" and "E" represent additional layers on the other side of the core layer. Layers "B" and "D" may be the same or

different, and layers "D" and "E" may be the same or different. A layer may also be absent. Additionally, structures containing more than five layers are contemplated, e.g., six, seven, eight, nine, and more layers are contemplated.

In order to modify or enhance certain properties of the multi-layer films of the invention for specific end-uses, it is possible for one or more of the layers to contain appropriate additives in effective amounts. Preferred additives include antistatic agents, antiblocking agents, lubricants, stabilizers and/or one or more of a class of hydrocarbons resins, such as alicyclic hydrocarbon resins which are known to improve barrier properties. Such additives are further described in U.S. Patent No. 5,254,394, which is incorporated herein by reference. It is useful to incorporate additives such as wax, finely divided inorganic antiblock particles, silicone oil, and silicone spheres such as non-migratory particulate crosslinked hydrocarbyl substituted polysiloxane slip agent, such as TOSPEARL which is marketed worldwide by Toshiba Silicone Co., Ltd. and in the United States by General Electric. The alicyclic hydrocarbons include polyterpenes, petroleum resins, and "hard" resins employed in the films to improve barrier properties and sealability. Examples of these materials would include PICCOLYTE and REGALREZ from Hercules, ZONTEC from Arizona Chemical Company, ARKON from Arakawa Chemical Co., and ESCOREZ from Exxon. Other additives that can be incorporated into one or more layers of the film include nucleators, such as MILLAD 3938 from Milliken for modifying the crystalline structure, and carbon black for brightening.

Finely divided inorganic antiblock materials, comprehended above, include, Syloid, a synthetic amorphous silica gel, having a composition of 99.7% SiO_2 ; diatomaceous earth having a composition of, for example, SiO_2 92%, Al_2O_3 3.3%, Fe_2O_3 1.2%, which can be obtained in various grades with average particle sizes ranging from about 0.5 microns to about 7-10 microns, which particles are porous and irregularly shaped; dehydrated kaolin clays, such as Kaopolite SF which has the composition SiO_2 55%, Al_2O_3 44%, Fe_2O_3 0.4% which has an average particle size of about 0.7 microns, and whose particles are thin flat platelets; and synthetic

precipitated silicates, Sipernat 44, for example, having a composition of SiO₂ 42%, Al₂O₃ 36%, Na₂O 22%, which has an average particle size of about 3-4 microns, which particles are porous and irregularly shaped. The amount of antiblock typically ranges from about 0.002 to about 0.5 weight % based upon the weight of the polymer.

Typically, a commercially available intensive mixer, such as those of the Bolling- or Banbury-type can be employed in mixing a concentrate of the finely divided inorganic material and the selected polymer until there is a uniform dispersion of the inorganic material in the polymer.

The alicyclic hydrocarbon is advantageously used to improve the barrier properties of the film. It has also been found that the alicyclic hydrocarbon contributes to film stiffness: the stiffness of the film increases as the amount of alicyclic hydrocarbon increases. The amount of alicyclic hydrocarbon employed in a layer of the film typically ranges from about 3 to about 15 wt.% based upon the weight of the layer.

One or more of the exposed layers of the multi-layer films of the present invention can be surface-treated to render the films receptive to printing inks, adhesives and/or coatings. The surface treatment can be carried out by any method known in the art such as corona discharge treatment or flame treatment.

Optionally a coating may be applied to one or both of the exposed surface(s) of the outermost layer(s) of the film. Prior to application of the coating material, the film may be surface treated or may be primed with a primer layer. Appropriate coatings contemplated include acrylic coatings such as those described in U.S. Patent Nos. 3,753,769 and 4,865,908, PVDC coatings such as those described in U.S. Patent No. 4,214,039; 4,447,494; 4,961,992; 5,019,447 and 5,057,177, all of which are incorporated herein by reference. A vinyl alcohol polymer, such as VINOL 325, may also be used as a coating composition.

Appropriate primer materials are poly(ethyleneimine), epoxy primer, and the like.

The outer surface of the film is preferably treated to increase its surface energy and therefor insure that the coating layer will be strongly adherent thereto, thereby reducing the possibility of the coating peeling or being stripped from the film. In addition to corona discharge and flame treatment, this treatment can be accomplished employing other known techniques, such as, for example, film chlorination, i.e., exposure of the film surface to aqueous chlorine, treatment with oxidizing agents such as chromic acid, hot air, or steam treatment, and the like. Although any of these techniques are effectively employed to pretreat the film surface, a particularly desirable method of treatment is the so-called electronic treatment method which comprises exposing the film surface to a high voltage corona discharge while passing the film between a pair of spaced electrodes. After electronic treatment of the film surface, the coating composition is then applied thereto.

The exposed, treated or untreated surface(s), e.g., the surface(s) of layer(s) A and/or E, may have applied to it/them coating compositions, as mentioned above, and/or substrates such as another polymer film or laminate; a metal foil such as aluminum foil; cellulosic webs, e.g. numerous varieties of paper such as corrugated paperboard, craft paper, glassines, cartonboard; nonwoven tissue, e.g., spunbonded polyolefin fiber, melt-blown microfibers, etc. The application may employ a suitable adhesive, e.g., a hot melt adhesive such as low density polyethylene, ethylene-methacrylate copolymer, water-based adhesive such as polyvinylidene chloride latex, and the like.

The extruded film can be stretched in the machine direction, coated with the coating composition and then stretched perpendicularly in the transverse direction. In yet another embodiment, the coating can be carried out after biaxial orientation is completed.

The coating composition should be applied in such amount that there will be deposited upon drying a smooth, evenly distributed layer, generally on the order of from about 0.01 to about 0.2 mil thickness (equivalent to about 0.2 to 3.5 g per 1000

sq. in. of film). In general, the thickness of the applied coating is such that it is sufficient to impart the desired seal sealability and/or oxygen and/or water vapor barrier characteristics to the resulting film. Generally, the coating comprises 1 to 25 wt%, preferably 7 to 15 wt% of the entire coated film composition. The coating on the film is subsequently dried by hot air, radiant heat or by any other convenient means.

There are many advantages to the film of the invention. However, most notable is the advantageous barrier properties which permit the film to be adapted to controlled atmosphere packaging. Additionally, the film has remarkable toughness and resistance to deformation but it also can be made with a soft, "drapy" feel which would be useful as a protective cover for clothing such as dry-cleaning bags.

Usually the film of the invention has a total thickness ranging from about 0.4 mil to about 2.5 mils, specifically from about 0.5 mil to about 2.0 mils. The thickness relationship of the layers can be important. In particular, the core layer is a relatively thick layer which constitutes about 40 to about 95 % of the total film thickness, an intermediate or tie layer may be of a thickness ranging from about 0 to about 50% of the total film thickness, while an outer skin layer may range from about 1 to about 15% of the total film thickness.

It is preferred that all layers of the multi-layer film structures of the present invention be coextruded. Thereafter, the film may be biaxially oriented.

The polymers are brought to the molten state and coextruded from a conventional extruder through a flat sheet die, the melt streams are combined in an adapter prior to being extruded from the die or within the die. After leaving the die, the multi-layer film is chilled and the quenched sheet is reheated and oriented.

The film is oriented by biaxially stretching the film. The film can be oriented by stretching from about 3.5 to about 6.5 times in the machine direction (MD) at temperatures ranging from about 110°C to about 150°C, and from about 5 to about

14 times in the transverse direction (TD) at temperatures ranging from about 152°C to about 165°C.

In each of the examples, the film was oriented about 4.5-6 times in the MD at a temperature of about 125-135°C and about 8-9 times in the TD at a temperature of about 155-160°C. Multi-layer films were prepared employing commercially available systems for coextrusion.

The properties of the films were determined according to the following methods:

A. Tensile Properties

10	1. Modulus (psi)	ASTM D882
	2. Elongation at Break (%)	ASTM D882
	3. Tensile Strength (psi)	ASTM D882

B. Dimensional Stability (% change): ASTM D1204

15

C. Optics:

1. Haze (% light transmitted)	ASTM D1003
2. Gloss (% light reflected at about a 45° angle)	ASTM D2457

20

D. WVTR (g/100 in²/day): ASTM F1249

E. TO₂ (g/100 in²/day): ASTM D3985

25 **F. Tear Strength (g/mil):** ASTM D1922

G. Coefficient of Friction (COF): ASTM D1894

H. Puncture Resistance (g/mil):

Standard Mobil PR Test

EXAMPLE 1

In Example 1, a five layer film was made having a core layer of syndiotactic polypropylene having a melt flow rate of about 7, tie layers of conventional isotactic polypropylene (Fina 3371) and a skin layer of ethylene-propylene-butene-1 terpolymer was applied to each outer surface of the tie layer. The core layer was 50% of the total film structure, the tie layers were 40% of the total film structure and the skin layers were 10% of the total film structure. The unoriented film measured 50-56 mils. The biaxially oriented film, oriented by conventional sequential biaxially orienting apparatus, measured about 1 mil in thickness.

The syndiotactic polypropylene was melted in an extruder to provide the core layer. A second and a third extruder, in association with the first extruder, were supplied with the isotactic polypropylene; these extruders provided the tie-layers. A fourth extruder, in association with the first three extruders, was supplied with ethylene-propylene-butene-1 terpolymer. A melt coextrusion was carried out maintaining the extruder at a temperature sufficient to maintain all polymers in the molten state (about 240 °C to about 270°C). The polymer extruded as the tie layers was maintained at about the same temperature as the polymer used in making the core layer, as was the terpolymer of the skin layers. The terpolymer of the fourth extruder was split into two streams to enable formation of skin layers on each surface of the tie layer.

EXAMPLE 2

In Example 2, a five layer film was made, following the procedure of Example 1, having a core layer of syndiotactic polypropylene, melt flow rate of about 7, tie layers of conventional isotactic polypropylene (Fina 3371) and skin layers of metallocene catalyzed polyethylene (Exxon product designated as Exxon 3016) located on each exposed surface of the tie layers. The core layer was 50% of the

total film thickness, the tie layers were 40% of the total film thickness and the skin layers were 10% of the total film thickness. The entire film was 1 mil.

The properties of the films of Examples 1 and 2 are reported in Table 1.

TABLE 1

EX.	Tensile Properties						Dimensional Stability			Coefficient of Friction			Optics		Water Vapor Trans Rate	Tear Strength	Puncture Resistance
	Modulus			Elongation			Ultimate Tensile			I/I	O/O	I/O	Haze	Gloss			
	MD	TD		MD	TD		MD	TD									
1	178	327		147	49		8.9	18.9	-6.9	0.81	0.83	0.85	2.3	86.7	0.52	14.4	1531
2	150	283		172	47		9.2	16.7	-7.4	0.37	0.58	0.45	3.1	90.7	0.52	12.6	1301

Note: "I/I," "O/O," and "I/O" designate "inside to inside," "outside to inside," "outside to outside," and "inside to outside" of the films, respectively.

Exempl 3

In Examl 3, five layer films were made by the process described in Example 1 having a core layer of syndiotactic polypropylene, melt flow rate of about 3. To the core layer was added 0, 3, 9, and 15 wt.%, based upon the weight of the core layer, of an alicyclic hydrocarbon, ARKON P115 from Arakawa Chemical Co. Tie layers of conventional isotactic polypropylene (Fina 3371) were coextruded on each side of the core layer and a skin layer of ethylene-propylene-butene-1 terpolymer was applied to each exposed surface of the tie layers. The core layer was 38% of the total film thickness, the tie layers were 52% of the total film thickness and the skin layers were 10% of the total film thickness. The entire film was about 1 mil in thickness. The properties of the films of this example are reported in Table 2.

TABLE 2

	Tensile Properties								Dimensional Stability		Coefficient of Friction		Optics		Barrier		Tear Strength		Puncture Resistance
	Modulus			Elongation			Ultimate Tensile												
	MD	TD		MD	TD		MD	TD											
% P115																			
0	170	331		159	39	9.0	19.8	-5.0	0.79	0.82	2.3	85.6	0.56	135.8	14.5	2.8		1550	
3	186	356		152	46	9.3	20.9	-3.5	0.76	0.85	2.7	85.3	0.52	132.9	14.2	2.4		1694	
9	222	405		182	50	12.2	22.1	-5.0	0.72	0.79	2.8	84.7	0.45	113.8	6.7	1.2		1820	
15	244	441		172	43	12.3	22.4	-5.7	0.80	0.80	2.9	86.5	0.40	105.7	5.6	1.9		2053	

Example 4

In Example 4, a five layer film was made following the procedure of Example 1 having a core layer of syndiotactic polypropylene, melt flow rate of about 3, 10 5 layers of conventional isotactic polypropylene (Fina 3371) and a skin layer on each side of the tie layer, which skin layers were metallocene catalyzed polyethylene commercially available from Exxon under the product designation 3016. This metallocene catalyzed polyethylene had a density of 0.910 and a melt index of 4.5. The skin layers each contained 2300 ppm silica antiblock (0.23 wt.% based on the 10 weight the skin layer). The silica antiblock additive was a commercial material sold under the product designation SYLOBLOC 42 by W.R. Grace & Co. The core layer was 50% of the total film structure and the tie layers were 40% of the total film structure while the skin layers were 10% of the total film structure. The entire film was 1 mil thick.

Example 5

Example 5 is substantially the same as Example 4, except that the skin layers were metallocene catalyzed polyethylene commercially available from Exxon under the product designation Exxon 3027. This metallocene catalyzed polyethylene had 20 a density of 0.908 and a melt index of 3.5.

Example 6

Example 6 is substantially the same as Example 4, except that the core layer propylene polymer had a melt flow of 7, and the skin layers were metallocene 25 catalyzed polyethylene commercially available from Exxon under the product designation Exxon 3034. This metallocene catalyzed polyethylene had a density of 0.902 and a melt index of 3.5.

The properties of each film of Examples 4, 5 and 6 are reported in Table 3.

TABLE 3

	Tensile Properties										Dimensional Stability	Coefficient of Friction			Optics		Water Vapor Trans. Rate	Tear Strength	Puncture Resistance	TO ₂
	Modulus			Elongation			Ultimate Tensile					I/I	O/O	I/O	Haze	Gloss				
	MD	TD	TD	MD	TD	MD	TD	MD	TD	TD										
EX.																				
4	143	227	146	42	8.9	11.6	-5.0	-13.9	0.49	0.47	0.47	0.47	2.5	85.8	0.59	13.5	5.8	1191	155	
5	148	227	140	59	9.2	12.1	-4.7	-14.2	0.55	0.54	0.57	0.57	1.7	90.8	0.6	12.3	4.9	1314	145	
6	167	273	131	39	9.5	13.8	-4.7	-13.2	0.55	0.55	0.55	0.55	1.5	82.2	0.58	11.3	4.2	1100	173	

Exempl 7

In Example 7, a three layer film was made having a core layer of syndiotactic polypropylene, melt flow rate of about 3, and outer layers made from conventional isotactic polypropylene (Fina 3371). The core layer was 50% of the total film structure while the skin layers were 50% of the total film structure. The film of this example was made by the process described in Example 1, except the fourth extruder was omitted. The entire film was about 1 mil thick.

The properties of this film are reported in Table 4.

TABLE 4

	Tensile Properties						Dimensional Stability		Optics		WVTR	Puncture Resistance
	Modulus		Elongation		Ultimate Tensile							
	MD	TD	MD	TD	MD	TD						
Ex.	MD	TD	MD	TD	MD	TD	MD	TD	Haze	Gloss		
7	187	321	139	48	10.8	16.9	-5.9	-15.9	0.9	91.5	0.53	1948

WHAT IS CLAIMED IS

1. A biaxially oriented multi-layer film which comprises:
 - (a) a core layer comprising a syndiotactic propylene polymer; and
 - 5 (b) at least one additional layer adjacent to the core layer comprising an ethylene or propylene homopolymer, an ethylene copolymer, a terpolymer containing propylene, ethylene, and butene-1 as comonomers, or a blend thereof.
- 10 2. The biaxially oriented multi-layer film of claim 1 which further comprises a coating and/or a skin layer adjacent to the at least one additional layer, the skin layer comprising a polyolefin.
- 15 3. The biaxially oriented multi-layer film of claim 1 in which the skin layer is a polyolefin selected from the group consisting of isotactic polypropylene, ethylene-propylene random copolymer, ethylene-propylene block copolymer or ethylene-propylene-butene-1 terpolymer.
- 20 4. The biaxially oriented multi-layer film of claim 2 in which the coating is selected from the group consisting of a polyvinylidene chloride coating, a polyvinyl alcohol coating and an acrylic polymer coating.
- 25 5. The biaxially oriented multi-layer film of claim 1 in which the at least one additional layer further comprises silica particles.
6. The biaxially oriented multi-layer film of claim 1 further comprising an alicyclic hydrocarbon.
7. A process for preparing an oriented multi-layer film which comprises the steps of:

- (a) method of coextruding a film comprising: (i) a core layer comprising syndiotactic polypropylene, and (ii) at least one additional layer adjacent the core layer comprising an ethylene or propylene homopolymer, an ethylene copolymer, a terpolymer containing propylene, ethylene and butene-1 as comonomers, or a blend thereof; and
- (b) orienting the coextruded combination in at least one direction.

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/US 00/07116

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 B32B27/32

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 B32B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 99 10172 A (MOBIL OIL CORP) 4 March 1999 (1999-03-04) claims 1-4 page 2, line 2 - line 13 page 4, line 15 - line 19 page 6, line 30 - page 7, line 2 page 7, line 12 - line 25	1-5,7
X	US 5 252 384 A (BOTHE LOTHAR ET AL) 12 October 1993 (1993-10-12) claims 1,3,4,12,13,20,22,25 column 4, line 46 - line 53	1,2,5,7
X	US 5 254 394 A (BOTHE LOTHAR ET AL) 19 October 1993 (1993-10-19) cited in the application claims 1,3,4,11-13,19 column 4, line 41 - line 48	1,2,5,7
	-/-	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

21 July 2000

Date of mailing of the international search report

31/07/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Girard, S

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 00/07116

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	<p>EP 0 732 197 A (KOHJIN CO) 18 September 1996 (1996-09-18) claim 1 page 2, column 2, line 28 - line 44 example 1</p>	1,7

INTERNATIONAL SEARCH REPORT

information on patent family members

International Application No

PCT/US 00/07116

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9910172 A	04-03-1999	AU 8410098 A EP 1007353 A	16-03-1999 14-06-2000
US 5252384 A	12-10-1993	DE 4035343 A DE 59106526 D EP 0484817 A ES 2079018 T FI 915214 A JP 5245992 A MX 9101938 A ZA 9108799 A	14-05-1992 26-10-1995 13-05-1992 01-01-1996 08-05-1992 24-09-1993 01-07-1993 29-07-1992
US 5254394 A	19-10-1993	DE 4035344 A DE 59106525 D EP 0484816 A ES 2079017 T FI 915213 A JP 5200957 A MX 9101939 A ZA 9108800 A	14-05-1992 26-10-1995 13-05-1992 01-01-1996 08-05-1992 10-08-1993 01-07-1993 29-07-1992
EP 0732197 A	18-09-1996	JP 8099394 A DE 69502172 D DE 69502172 T US 5620803 A WO 9609931 A	16-04-1996 28-05-1998 13-08-1998 15-04-1997 04-04-1996